

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 8/18, 8/34, 255/02	A1	(11) International Publication Number: WO 98/31716 (43) International Publication Date: 23 July 1998 (23.07.98)
(21) International Application Number: PCT/US98/00946 (22) International Filing Date: 20 January 1998 (20.01.98) (30) Priority Data: 60/035,873 22 January 1997 (22.01.97) US (71) Applicant (for all designated States except US): E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): DRYSDALE, Neville, Everton [JM/US]; 227 Welsh Tract Road, Newark, DE 19702 (US). WANG, Lin [CN/US]; 112 Brook Run, Hockessin, DE 19707 (US). YANG, Zhen, Yu [CN/US]; 2609 Marhill Drive, Wilmington, DE 19810 (US). (74) Agent: SIEGELL, Barbara, C.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		(81) Designated States: AL, AM, AU, AZ, BA, BB, BG, BR, BY, CA, CN, CU, CZ, EE, GE, GW, HU, ID, IL, IS, JP, KG, KP, KR, KZ, LC, LK, LR, LT, LV, MD, MG, MK, MN, MX, NO, NZ, PL, RO, RU, SG, SI, SK, SL, TJ, TM, TR, TT, UA, US, UZ, VN, YU, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: GRAFTING OF POLYMERS WITH FLUOROCARBON COMPOUNDS (57) Abstract Fluorine containing terminal olefins may be grafted onto polymers containing hydrogen bound to carbon in the presence of free radicals. The olefins may also contain other functional groups. The resulting novel grafted polymers are useful as molding resins, for coating and as catalysts.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

TITLE

GRAFTING OF POLYMERS WITH FLUOROCARBON COMPOUNDS

FIELD OF THE INVENTION

Fluorine containing olefins can be grafted onto polymers containing
5 carbon-hydrogen bonds in the presence of a source of free radicals. The resulting
grafted polymers have unique structures, and may be used as catalysts.

TECHNICAL BACKGROUND

Organic polymers containing fluorine substitution have traditionally been
made by (co)polymerizing one or more fluorine containing monomers, optionally
10 with unfluorinated monomers. It is well known that polymers containing large
amounts of fluorine often have desirable properties, such as improved heat and/or
chemical resistance. However, polymers containing only relatively small amounts
of fluorine also often have desirable properties (compared to unfluorinated
polymers), such as altered surface properties or being useful as catalysts.
15 Therefore versatile, cost effective methods of making polymers with relatively
low fluorine contents are desired.

SUMMARY OF THE INVENTION

This invention concerns a process for producing a partially fluorinated
polymer, comprising, contacting in the liquid phase a first polymer with contains
20 hydrogen bound to carbon with a compound of the formula $H_2C=CHCR^1R^2R^6Y$,
and a source of free radicals, wherein:

R^1 and R^2 are each independently fluorine or perfluoroalkyl
containing 1 to 20 carbon atoms;

R^6 is fluorinated alkylene containing 1 to 20 carbon atoms and
25 optionally containing one or more ether groups or alkylene containing 1 to 20
carbon atoms and optionally containing one or more ether groups; and

Y is hydrogen or a functional group;

and provided that said contacting is carried out at a temperature at which
said source of free radicals generates free radicals.

30 This invention also concerns a polymer, comprising, branches having the
formula $-CH_2-CH_2CR^1R^2R^6Y$, wherein:

R^1 and R^2 are each independently fluorine or perfluoroalkyl
containing 1 to 20 carbon atoms;

R^6 is fluorinated alkylene containing 1 to 20 carbon atoms and
35 optionally containing one or more ether groups or alkylene containing 1 to 20
carbon atoms and optionally containing one or more ether groups; and

Y is hydrogen or a functional group;

and provided that a main chain of said polymer contains hydrogen bound
to carbon.

DETAILS OF THE INVENTION

Herein certain terms are used, and they are defined below:

By "fluorinated alkylene" is meant an alkylene group containing one or more fluorine atoms.

5 By a "functional group" is meant any univalent group, as defined in R. T. Morrison, et al., Organic Chemistry, 6th Ed., Prentice hall, Englewood Cliffs, NJ, 1992, p. 167-168, and is an atom or group of atoms that defines the structure of a particular family of organic compounds and, at the same time, determines (at least partially) their properties. Any functional group present should not interfere
10 with any contemplated reaction such as the grafting described above, nor should it result in any compound in which it is present being unusably unstable.

By "grafting herein" is meant attachment of a branch to a preexisting polymer. Herein a branch will usually be monomeric, i.e., contain only one of the grafting molecules.

15 By a "source of free radicals" is meant any compound or other means of generating free radicals such as ionizing radiation. If the free radicals are generated thermally, then the grafting reaction takes place at temperatures at which the source of free radicals reacts to form free radicals.

By "containing one or more ether groups" means containing one or more
20 ether oxygen atoms between alkylene segments.

By hydrocarbyl is meant a univalent group containing on carbon and hydrogen. By substituted hydrocarbyl is meant a hydrocarbyl group containing one or more functional groups.

The grafting process described herein takes place in the liquid phase. This
25 means that all of the ingredients are in the liquid phase at the time of the grafting reaction. However this does not mean that all of the ingredients must be in the same liquid phase, nor does it mean that any additional liquids must be present (such as a "solvent") during the process. The polymer itself and/or the fluorinated compound to be grafted may be liquids and liquify the other component. If a
30 chemical free radical source is used, it too may be a liquid or dissolve in one of the other components, but it will often be present in relatively small quantities, and so unable to dissolve the other components.

Useful groups Y include $-\text{SO}_2\text{F}$, $-\text{CO}_2\text{R}^3$, $\text{P}(\text{O})(\text{OR}^3)_2$, SO_3H , and $-\text{S}(\text{O})_2\text{NHS}(\text{O})_2\text{R}^4$, wherein each R^3 is independently hydrocarbyl or substituted
35 hydrocarbyl containing 1 to 20 carbon atoms, and R^4 is perfluoroalkyl containing 1 to 20 carbon atoms. In a preferred compound or polymer, Y is halogen, more preferably fluorine; sulfonyl fluoride; sulfonic acid; or hydrogen.

In preferred compounds and polymers R^6 contains 1 to 50 carbon atoms. Preferred groups R^6 are perfluoroalkylene or ether substituted perfluoroalkylene, and especially preferably $-(CF_2)_d-$ wherein d is 2 to 20 and $-CF_2OCF_2CF_2-$.

Sources of free radicals are well known in the art, see for instance

- 5 J. Brandrup, et al., Ed., Polymer Handbook, 3rd Ed., John Wiley & Sons, New York, 1989, p. II-1 to II-65 and H. Mark, et al., Ed., Encyclopedia of Polymer Science and Engineering, vol. 13, John Wiley & Sons, New York, 1988, p. 754-789 both of which are hereby included by reference. These "sources" may be chemical compounds such as peroxides or other means of generating free
- 10 radicals, such as ionizing radiation. Most commonly chemical compounds which are sources of free radicals will be used. These compounds may form free radicals by any method, for instance by decomposing thermally to form free radicals, or by the reaction of a redox couple to form free radicals. Thermal decomposition of a free radical source is a preferred method of forming free radicals. Useful sources
- 15 of free radicals include compounds such as t-butyl peroxide and benzoyl peroxide. If a compound is used as a free radical source, relatively small amounts are usually used, about 0.1 to about 25 mole percent, preferably about 1 to 10 mole percent, of the grafting molecule present being typical.

- The amount of grafting molecule, $H_2C=CHCR^1R^2R^6Y$, grafted onto the
- 20 polymer will vary according to the amount of $H_2C=CHCR^1R^2R^6Y$ relative to the polymer, the amount of free radical source present, and the efficiency of the grafting process. It is preferred that about 1 g to about 5000 g, more preferably about 500 g to about 2000 g, of grafting molecule per kg of ungrafted (starting) polymer actually be grafted onto the polymer. In another preferred process and its
- 25 resulting polymer, the grafted polymer has more hydrogen atoms than fluorine atoms, more preferably the ratio of hydrogen atoms to fluorine atoms is about 3 or more, especially preferably about 5 to about 150.

- The polymers which may be grafted in the process described herein, i.e., are suitable, are those which do not suffer so much decomposition, typically
- 30 lowering of molecular weight, in the presence of free radicals as to render the final product unusable. It is well known in the art, see for instance H. Mark, et al., Ed., Encyclopedia of Polymer Science and Engineering, vol. 13, John Wiley & Sons, New York, 1988, p. 667-682, that some polymers are relatively stable in the presence of free radicals, while others may undergo chain scission and lowering of
- 35 molecular weight relatively easily. For example linear polyethylene is thought of as relatively stable, while most polypropylenes are thought to be relatively unstable.

Nevertheless, even "relatively unstable" polymers may be grafted under some circumstances. For instance, when it is desired to graft only a small amount

of $\text{H}_2\text{C}=\text{CHCR}^1\text{R}^2\text{R}^6\text{Y}$ onto the polymer, only small amounts of free radical source may be needed, and the resulting loss of molecular weight (if any) in the polymer being grafted may be acceptable in the application contemplated.

Exposure to free radicals may also crosslink some polymers, depending on the conditions. A situation such as this may also be acceptable, since crosslinked polymers may be desired. For instance if used as a catalyst, the insolubility of a crosslinked polymer may be an advantage in recovering the polymer after use. Indeed in the process described herein a crosslinked polymer may be used as the starting polymer. In this instance it may be desirable to swell the crosslinked polymer with another compound or with $\text{H}_2\text{C}=\text{CHCR}^1\text{R}^2\text{R}^6\text{Y}$ and/or the free radical source to obtain more uniform grafting.

Preferred polymers to be grafted include polyethylene, especially (relatively) linear polyethylene, polyethers such as poly(tetramethylene ether) glycol, and ethylene copolymers such as ethylene/vinyl acetate copolymer and ethylene/methyl acrylate copolymer.

Reactions may be performed on the grafted polymer after the grafting reaction. For instance, functional groups grafted onto the polymer may be transformed into other functional groups.

The grafted polymers described herein may be used as molding resins, in coatings, or be used to form films. They may be blended with other polymers to modify those other polymers characteristics, such as surface properties. Grafted polymers containing functional groups may be useful as catalysts, see for instance Experiment 4.

In the Examples and Experiments, the following abbreviations are used:

3-Me-THF - 3-methyltetrahydrofuran
DSC - differential scanning calorimetry
Mn - number average molecular weight
Mw - weight average molecular weight
mp - melting point
PD - polydispersity, Mw/Mn
RT - room temperature
TGA - thermogravimetric analysis
THF - tetrahydrofuran
Tm - melting point (for a polymer)

In all TGA analyses, the heating rate was $20^\circ\text{C}/\text{min}$, unless otherwise noted.

EXPERIMENT 1Preparation Of $\text{ICH}_2\text{CH}_2\text{CF}_2\text{CF}_2\text{OCF}_2\text{CF}_2\text{SO}_2\text{F}$

A mixture of 213 g of $\text{ICF}_2\text{CF}_2\text{OCF}_2\text{CF}_2\text{SO}_2\text{F}$, 0.5 g of limonene and 30 g of $\text{CH}_2=\text{CH}_2$ was heated in an autoclave at 210°C for 8 hours. Distillation of the mixture gave 187.3 g of title compound, bp 88-89°C/4 kPa. ^{19}F NMR: +45.0 (t, J = 5.7 Hz, 1F), -82.7 (m, 2F), -87.2 (m, 2F), -112.7 (m, 2F), -119.3 (t, J = 17.0 Hz, 2F).

EXPERIMENT 2Preparation Of $\text{CH}_2=\text{CHCF}_2\text{CF}_2\text{OCF}_2\text{CF}_2\text{SO}_2\text{F}$

To a stirred solution of 136.2 g (0.3 mol) of $\text{ICH}_2\text{CH}_2\text{CF}_2\text{CF}_2\text{OCF}_2\text{CF}_2\text{SO}_2\text{F}$ and 200 mL of CH_3CN was slowly added 38 g (0.376 mol) of Et_3N at 75 to 80°C over 6 hours. The reaction mixture was neutralized with conc. H_2SO_4 at 0°C, and then poured into water and extracted with ether. The ether layer was washed with water and dried over MgSO_4 . After removal of the ether, a residue was distilled to give 65.3 g of pure product, bp 115-117°C. ^{19}F NMR: +45.1 (m, 1F), -82.5 (m, 2F), -87.8 (m, 2F), 112.5 (m, 2F), -118.0 (m, 2F). ^1H NMR: 5.80-6.05 (m).

EXAMPLE 1Grafting Of Polyethylene With $\text{CH}_2=\text{CHCF}_2\text{CF}_2\text{OCF}_2\text{CF}_2\text{SO}_2\text{F}$

A four-necked flask fitted with a condenser and an additional funnel was charged with 7.5 g polyethylene (Hoechst wax PE-130, number average molecular weight of 3000), 16.3 g of $\text{CH}_2=\text{CHCF}_2\text{CF}_2\text{OCF}_2\text{CF}_2\text{SO}_2\text{F}$ and 60 mL of 1,2-dichlorobenzene. After the apparatus was partially evacuated and refilled with argon for several times, the flask was heated to 140°C until all of the polyethylene dissolved, and then cooled to 120°C. A solution of 1.23 g of di-t-butyl peroxide in 20 mL of 1,2-dichlorobenzene was slowly added over 5 h. After the addition was complete, the reaction mixture was stirred for 8 h. The hot solution with white solids was poured into 600 mL of acetone to precipitate the polymer. Filtration and wash with acetone gave white solids which were dried at room temperature in vacuum to give 16.3 g of grafted polymer. IR (KBr): 1460 cm^{-1} (s, SO_2F), 1205-1110 cm^{-1} (s, C-F). Elemental analysis revealed that the polymer contained 3.94% sulfur, which indicated that equivalent weight of the polymer per $-\text{SO}_2\text{F}$ group was 813. Melting point of the polymer by DSC was 115°C and 10% weight loss by TGA was at 380°C in nitrogen.

EXAMPLE 2Grafting Of High Density Polyethylene With $\text{CH}_2=\text{CHCF}_2\text{CF}_2\text{OCF}_2\text{CF}_2\text{SO}_2\text{F}$

A four-necked flask fitted with a condenser and an additional funnel was charged with 7.5 g high density polyethylene (Aldrich Chemical Co., Milwaukee, WI, USA), Mw = 125000, 16.3 g of $\text{CH}_2=\text{CHCF}_2\text{CF}_2\text{OCF}_2\text{CF}_2\text{SO}_2\text{F}$ and 80 mL

of 1,2-dichlorobenzene. After the apparatus was partially evacuated and refilled with argon several times, the flask was heated to 140°C until all of the polyethylene dissolved, and then cooled to 125°C (very viscous solution). A solution of 1.23 g of di-t-butyl peroxide in 20 mL of 1,2-dichlorobenzene was added over 7 h. After the addition was complete, the reaction mixture was heated at 130°C overnight. The hot solution with white solids was poured into 600 mL of acetone to precipitate the polymer, which was cut in the presence of wet ice in a blender to 16.7 g of fine power polymer.

EXAMPLE 3

Preparation Of A Sulfonic Acid-Containing Polymer

A mixture of 8.0 g of the grafted polymer of Example 1, 2.5 g of KOH, 15 mL of ethanol, 5 mL of THF and 2 mL of water was stirred at room temperature overnight and at 70°C for 2 h. After removal of volatiles, the residue was treated with conc. HCl for 30 minutes, filtered, washed with water and aq. HCl and dried at 60°C in vacuum for 24 h to give 6.7 g of solids, which could be pressed to film at 135°C.

EXAMPLE 4


Preparation Of A Sulfonic Acid-Containing Polymer

A mixture of 14.0 g of the grafted polymer of Example 2, 4.5 g of KOH, 50 mL of ethanol, 10 mL of THF and 3 mL of water was stirred at 60°C for 5 h, and then at room temperature overnight. After removal of volatiles, residue was treated with conc. HCl for 40 minutes, filtered, washed with water and aq. HCl, and dried at 70°C in a vacuum for 8 h to give 13.2 g of solids. MP by DSC was 105°C and 10% weight loss by TGA was at 230°C in N₂. The solids could be pressed to a film at 135°C. Elemental analysis revealed that catalyst contained 3.19% sulfur, which indicated that the polymer acid equivalent weight was around 1000.

EXPERIMENT 3

Synthesis Of Highly Branched Polyethylene

The compound



wherein BAF is tetrakis(3,5-trifluoromethylphenyl)borate (0.2952 g, 0.2 mmol) was dissolved in 200 mL CH_2Cl_2 in a Schlenk flask in a drybox. The flask was connected to a Schlenk line and the flask was then briefly evacuated and refilled with ethylene from the Schlenk line. This was stirred at RT under 101 kPa of ethylene for 18 h. Methanol (1200 mL) was then added to the solution, which resulted in precipitation of an oil. The oil was isolated, dissolved in 500 mL hexanes and was filtered through silica gel. Evaporation of hexanes and drying under vacuum gave 40 g of clear oil. ^1H NMR analysis (CD_2Cl_2): 124 methyls per 1000 methylene carbons. δ 0.8-1.0 ppm, $-\text{CH}_3$, 1.1-1.4 ppm, $-\text{CH}_2-$ and $-\text{CH}-$. The polymer exhibited a glass transition temperature of -63°C by DSC. GPC (THF, polystyrene standard): $M_w = 108,000$, $M_n = 69,800$, $\text{PD} = 1.55$.

EXAMPLE 5

Grafting $\text{CH}_2=\text{CH}(\text{CF}_2)_2\text{O}(\text{CF}_2)_2\text{SO}_2\text{F}$ Onto Highly Branched Polyethylene

Highly branched polyethylene of Experiment 3 (13.6 g) and $\text{CH}_2=\text{CH}(\text{CF}_2)_2\text{O}(\text{CF}_2)_2\text{SO}_2\text{F}$ (29.6 g, 90.8 mmol) were dissolved in 85 mL o-dichlorobenzene at 125°C . An o-dichlorobenzene solution of t-butyl peroxide (2.8 g in 30 mL o-dichlorobenzene) was added over a period of 8 h at 125°C with stirring. The solution was then allowed to stir at 125°C overnight. It was then cooled to RT and was poured into 400 mL methanol with stirring. The oil was isolated, washed with 3X100 mL methanol and was dried under vacuum at 70°C for 6 h. A yellow viscous oil (38.14 g) was obtained. Comparison of the integral of the CH_2CF_2- (2.00 ppm based on ^1H NMR in a solvent of CD_2Cl_2) with the integrals of methyls (0.8-1.0 ppm) and methylenes (1.1-1.4 ppm) indicated a graft comonomer content of 13.0 mol%. ^{19}F NMR(CD_2Cl_2): 46.2 ppm, $-\text{SO}_2\text{F}$; -81.2 ppm, -86.4 ppm, -111.1 ppm, -117.4 ppm, CF_2 peaks. The polymer exhibited a glass transition temperature of -53°C by DSC. GPC (THF, polystyrene standard): $M_w = 87,200$, $M_n = 51,000$, $\text{PD} = 1.71$.

EXAMPLE 6

Preparation Of A Potassium Sulfonate-Containing Polymer

The grafted polymer of Example 5 (23.64 g) was mixed with 10 g KOH, 70 mL THF, 60 mL ethanol and 5 mL water. Stirring the mixture at RT resulted in hydrolysis of the SO_2F group. After stirring at RT for 2 h, this mixture was refluxed for 6 h. Solvent was then evaporated under vacuum at 60°C for 8 h. The solid was dissolved in 400 mL acetone. The mixture was filtered through Celite®. To the filtrate was added 400 mL THF. This mixture was filtered through Celite®. Evaporation of solvents and vacuum drying gave 17.7 g a brittle yellow

orange solid. This solid dissolves in water at RT. Its water solution is neutral based.

EXAMPLE 7

Preparation Of A Sulfonic Acid-Containing Polymer

- 5 The product of Example 6 (15.0 g) was mixed with 80 mL of conc. HCl. This was vigorously stirred for 12 h. The resulting solid was filtered, washed with 2X5 mL conc. HCl and dried under vacuum at 70°C for 6 h. A red solid (8.5 g) was obtained.

EXAMPLE 8

- 10 Grafting $\text{CH}_2=\text{CH}(\text{CF}_2)_2\text{O}(\text{CF}_2)_2\text{SO}_2\text{F}$ Onto Poly(Tetramethylene Ether) Glycol

- An o-dichlorobenzene solution of *t*-butyl peroxide (0.60 g peroxide in 7 mL o-dichlorobenzene) was slowly added to a solution of PTMEG (Mw = 11,700, Mn = 8,290, polystyrene standard, THF) in o-dichlorobenzene (3.56 g in 20 mL o-dichlorobenzene) at 125°C. The addition was completed in 2.5 h. The solution was allowed to stir at 125°C for another 6 h. Volatiles were evaporated at 125°C under full vacuum for 5 h, leaving 9.68 g of a white viscous oil as the product. ^{19}F NMR(CD_2Cl_2): 44.5 ppm, $-\text{SO}_2\text{F}$; -82.8 ppm, -88.2 ppm, -112.8 ppm, -119.4 ppm, CF_2 peaks. The polymer exhibited a glass transition temperature of -68°C by DSC. GPC (THF, polystyrene standard): Mw = 27,800, Mn = 11,300, PD = 2.46.

EXAMPLE 9

Preparation Of A Potassium Sulfonate-Containing Polymer

- To a mixture of 9.67 g of the product of Example 8, and 2.5 g KOH was added 20 mL THF, 15 mL ethanol and 1.5 mL water. Stirring at RT resulted an exothermic reaction. This was allowed to stir at RT for 1 h and was then refluxed for 5 h. The solvents were evaporated under vacuum. The solid was extracted with 100 mL acetone. This mixture was filtered through Celite®, followed by 3X10 mL acetone wash. To the filtrate was added 130 mL THF. This was filtered through Celite®. Evaporation of the solvents and drying under vacuum at 105°C overnight gave 8.8 g of a brittle yellow solid. This product dissolves in water at RT to form a solution that is neutral.

EXAMPLE 10

Preparation Of A Sulfonic Acid-Containing Polymer


- To 4.23 g of the polymer of Example 9 in a flask was added 20 mL conc. HCl. This mixture was allowed to vigorously stir for 20 min at RT. The top layer was decanted. This procedure was repeated another two times using 15 mL of conc. HCl. The viscous oil was dried at 105°C under full vacuum for 6.5 h. A dark red viscous oil (2.41 g) was obtained.

EXAMPLE 11

The potassium salt of a hydrolyzed $\text{CH}_2=\text{CH}(\text{CF}_2)_2\text{O}(\text{CF}_2)_2\text{SO}_2\text{F}$ grafted polyethylene (13 mol% of grafted comonomer, $M_w = 97,600$, $M_n = 67,100$) is soluble in water. The potassium salt of the hydrolyzed ethylene copolymer of

5 $\text{CH}_2=\text{CH}(\text{CH}_2)_4(\text{CF}_2)_4\text{O}(\text{CF}_2)_2\text{SO}_2\text{F}$ made with a Pd catalyst (8.5 mol% of comonomer, $M_w = 120,000$, $M_n = 78,900$) is not very soluble in water.

The polymer made with the Pd catalyst was made by using the compound



10

as the catalyst, and (0.0205 g, 0.024 mmol) and $\text{CH}_2=\text{CH}(\text{CH}_2)_4(\text{CF}_2)_4\text{O}(\text{CF}_2)_2\text{F}$ (3.5 g, 7.26 mmol) were dissolved in 18 mL CH_2Cl_2 in a Schlenk flask in a drybox. The flask was connected to a Schlenk line and the flask was then briefly evacuated and refilled with ethylene from the Schlenk line. This was stirred at RT

15 under 101 kPa of ethylene for 72 hr. Solvent was evaporated after filtration. The viscous oil was dissolved in 10 mL CH_2Cl_2 , followed by addition of 100 mL methanol. The upper layer was decanted. The reverse precipitation was repeated two more time, followed by vacuum drying to yield 3.68 g of a light yellow viscous oil. GPC (THF, polystyrene standard): $M_w = 120,000$, $M_n = 78,900$,

20 $P/D = 1.54$. The turnover numbers for ethylene and the comonomer are 2098 and 195, respectively. The polymer was hydrolyzed to produce a sulfonic acid containing polymer.

EXPERIMENT 4Polymerization Of A Cyclic Ether

25 In a dry box, the product of Example 4 (0.50 g), THF (3.0 g), THF/3-Me-THF (55/45 mol %, 7.00 g) and acetic anhydride (0.50 g) were placed in a 20 mL vial equipped with a stirring bar. After stirring for one h at room temperature, the vial was removed from the dry box and the polymerization terminated by the addition of THF, water (1.00 mL) and ether. The solids were

30 removed via filtration and the resulting filtrate concentrated at reduced pressure and then dried under vacuum, affording 2.91 g of polymer. GPC analysis (PS STD.): $M_n = 11300$, $M_w = 16800$, $PD = 1.48$.

CLAIMS

What is claimed is:

1. A process for producing a partially fluorinated polymer, comprising, contacting in the liquid phase a first polymer with contains hydrogen bound to carbon with a compound of the formula $H_2C=CHCR^1R^2R^6Y$, and a source of free radicals, wherein:
 - R^1 and R^2 are each independently fluorine or perfluoroalkyl containing 1 to 20 carbon atoms;
 - R^6 is fluorinated alkylene containing 1 to 20 carbon atoms and optionally containing one or more ether groups or alkylene containing 1 to 20 carbon atoms and optionally containing one or more ether groups; and
 - Y is hydrogen or a functional group;
 and provided that said contacting is carried out at a temperature at which said source of free radicals generates free radicals.
2. A polymer, comprising, branches having the formula $-CH_2-CH_2CR^1R^2R^6Y$, wherein:
 - R^1 and R^2 are each independently fluorine or perfluoroalkyl containing 1 to 20 carbon atoms;
 - R^6 is fluorinated alkylene containing 1 to 20 carbon atoms and optionally containing one or more ether groups or alkylene containing 1 to 20 carbon atoms and optionally containing one or more ether groups; and
 - Y is hydrogen or a functional group;
 and provided that a main chain of said polymer contains hydrogen bound to carbon.
3. The process or polymer as recited in Claim 1 or 2 wherein R^6 is perfluoroalkylene or ether substituted perfluoroalkylene.
4. The process or polymer as recited in Claim 1 or 2 wherein R^6 is $-(CF_2)_d-$ wherein d is 2 to 20 or $-CF_2OCF_2CF_2-$.
5. The process or polymer as recited in Claim 1 or 2 wherein Y is fluorine, sulfonyl fluoride, sulfonic acid, or hydrogen.
6. The process or polymer as recited in Claim 1 or 2 wherein Y is $-SO_2F$.
7. The polymer as recited in Claim 2 wherein R^6 is $-(CF_2)_d-$ wherein d is 2 to 20 or $-CF_2OCF_2CF_2-$, and Y is SO_2F , SO_3M or SO_3H , wherein M is an alkali metal.
8. The process or polymer as recited in Claim 3 wherein Y is $-SO_2F$.

INTERNATIONAL SEARCH REPORT

Int. .tional Application No

PCT/US 98/00946

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08F8/18 C08F8/34 C08F255/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 018, no. 163 (C-1181), 18 March 1994 & JP 05 331242 A (SANYO CHEM IND LTD), 14 December 1993,	1-5
Y	see abstract	6-8
X	PATENT ABSTRACTS OF JAPAN vol. 017, no. 644 (C-1134), 30 November 1993 & JP 05 202148 A (MITSUI PETROCHEM IND LTD), 10 August 1993,	1-5
Y	see abstract	6-8
Y	US 4 384 941 A (OKAMOTO JIRO ET AL) 24 May 1983 see column 2, line 15 - column 3, line 52; example 3	6-8



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

1 April 1998

Date of mailing of the international search report

09/04/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Rodriguez, L

INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. l. Application No

PCT/US 98/00946

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4384941 A	24-05-83	JP 1370122 C	25-03-87
		JP 57131376 A	14-08-82
		JP 61034515 B	08-08-86
		CA 1185558 A	16-04-85
		FR 2499594 A	13-08-82
		GB 2094835 A,B	22-09-82
<hr/>			